X7R Dielectric, 6.3 – 250 VDC (Commercial Grade)



Overview

KEMET's X7R dielectric features a 125°C maximum operating temperature and is considered temperature stable. The Electronics Components, Assemblies and Materials Association (EIA) characterizes X7R dielectric as a Class II material. Components of this classification are fixed, ceramic dielectric capacitors suited for bypass and decoupling applications or for frequency discriminating

circuits where Q and stability of capacitance characteristics are not critical. X7R exhibits a predictable change in capacitance with respect to time and voltage, boasting a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to ±15% from -55°C to +125°C.

Benefits

- -55°C to +125°C operating temperature range
- · Lead (Pb)-free, RoHS, and REACH Compliant
- · Temperature stable dielectric
- EIA 0402, 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, and 2225 case sizes
- DC voltage ratings of 6.3 V, 10 V, 16 V, 25 V, 35 V, 50 V, 100 V, 200 V, and 250 V
- Capacitance offerings ranging from 10 pF to 47 μF
- Available capacitance tolerances of ±5%, ±10% and ±20%
- Non-polar device, minimizing installation concerns
- 100% pure matte tin-plated termination finish allowing for excellent solderability
- SnPb termination finish option available upon request (5% Pb minimum)



Applications

Typical applications include decoupling, bypass, filtering and transient voltage suppression.



Ordering Information

С	1206	С	106	M	4	R	A	С	TU
Ceramic	Case Size (L" x W")	Specification/ Series ¹	Capacitance Code (pF)	Capacitance Tolerance	Rated Voltage (VDC)	Dielectric	Failure Rate/ Design	Termination Finish ²	Packaging/ Grade (C-Spec)
	0402 0603 0805 1206 1210 1808 1812 1825 2220 2225	C = Standard	Two significant digits and number of zeros.	J = ±5% K = ±10% M = ±20%	9 = 6.3 8 = 10 4 = 16 3 = 25 6 = 35 5 = 50 1 = 100 2 = 200 A = 250	R = X7R	A = N/A	C = 100% Matte Sn	See "Packaging C-Spec Ordering Options Table"

¹ Flexible termination option is available. Please see FT-CAP product bulletin C1013_X7R_FT-CAP_SMD.

Packaging C-Spec Ordering Options Table

Packaging Type ¹	Packaging/Grade Ordering Code (C-Spec)
Bulk Bag/Unmarked	Not required (Blank)
7" Reel/Unmarked	TU
13" Reel/Unmarked	7411 (EIA 0603 and smaller case sizes) 7210 (EIA 0805 and larger case sizes)
7" Reel/Marked	TM
13" Reel/Marked	7040 (EIA 0603 and smaller case sizes) 7215 (EIA 0805 and larger case sizes)
7" Reel/Unmarked/2 mm pitch ²	7081
13" Reel/Unmarked/2 mm pitch ²	7082

¹ Default packaging is "Bulk Bag." An ordering code C-Spec is not required for "Bulk Bag" packaging.


² Additional termination finish options may be available. Contact KEMET for details.

¹ The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. Please contact KEMET if you require a laser marked option. For more information see "Capacitor Marking."

² The 2 mm pitch option allows for double the packaging quantity of capacitors on a given reel size. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information."



Dimensions - Millimeters (Inches)



EIA Size Code	Metric Size Code	L Length	W Width	T Thickness	B Bandwidth	S Separation Minimum	Mounting Technique
0402	1005	1.00 (0.040) ±0.05 (0.002)	0.50 (0.020) ±0.05 (0.002)		0.30 (0.012) ±0.10 (0.004)	0.30 (0.012)	Solder reflow only
0603	1608	1.60 (0.063) ±0.15 (0.006)	0.80 (0.032) ±0.15 (0.006)		0.35 (0.014) ±0.15 (0.006)	0.70 (0.028)	
0805	2012	2.00 (0.079) ±0.20 (0.008)	1.25 (0.049) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)	0.75 (0.030)	Solder wave or Solder reflow
1206	3216	3.20 (0.126) ±0.20 (0.008)	1.60 (0.063) ±0.20 (0.008)		0.50 (0.02) ±0.25 (0.010)		
1210¹	3225	3.20 (0.126) ±0.20 (0.008)	2.50 (0.098) ±0.20 (0.008)	See Table 2	0.50 (0.02) ±0.25 (0.010)		
1808	4520	4.70 (0.185) ±0.50 (0.020)	2.00 (0.079) ±0.20 (0.008)	for Thickness	0.60 (0.024) ±0.35 (0.014)		
1812	4532	4.50 (0.177) ±0.30 (0.012)	3.20 (0.126) ±0.30 (0.012)		0.60 (0.024) ±0.35 (0.014)	N/A	Solder reflow
1825	4564	4.50 (0.177) ±0.30 (0.012)	6.40 (0.252) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		only
2220	5650	5.70 (0.224) ±0.40 (0.016)	5.00 (0.197) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		
2225	5664	5.60 (0.220) ±0.40 (0.016)	6.40 (0.248) ±0.40 (0.016)		0.60 (0.024) ±0.35 (0.014)		

 $^{^{1}}$ For capacitance values ≥ 4.7 μF add 0.02 (0.001) to the width tolerance dimension and 0.10 (0.004) to the length tolerance dimension.

Qualification/Certification

Commercial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

Environmental Compliance

Lead (Pb)-free, RoHS, and REACH compliant without exemptions.



Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC)	±15%
¹ Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
² Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5 ±1 seconds and charge/discharge not exceeding 50mA)
³ Dissipation Factor (DF) Maximum Limit at 25°C	See Dissipation Factor Limit Table
⁴ Insulation Resistance (IR) Minimum Limit at 25°C	See Insulation Resistance Limit Table (Rated voltage applied for 120 ±5 seconds at 25°C)

¹Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 48 or 1,000 hours. Please refer to a part number specific datasheet for referee time details.

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

Insulation Resistance Limit Table

EIA Case Size	Rated DC Voltage	1,000 megohm microfarads or 100 GΩ	500 megohm microfarads or 10 GΩ	100 megohm microfarads or 10 GΩ
0402	ALL	< 0.012 µF	≥ 0.012 µF	N/A
0603	≤ 200 V	< 0.047 µF	≥ 0.047 µf < 0.47 µf	≥ 0.47 µf
0003	250 V	N/A	N/A	ALL
0805	≤ 200 V	< 0.15 μF	≥ 0.15 µF < 2.2 µf	≥ 2.2 µf
0805	250 V	< .027 μF	N/A	≥ .027 µF
1006	≤ 200 V	< 0.47 μF	≥ 0.47 µF < 4.7 µf	≥ 4.7 µf
1206	250 V	< 0.12 µF	N/A	≥ 0.12 µF
1010	≤ 200 V	< 0.39 µF	≥ 0.39 µF < 10 µf	≥ 10 µf
1210	250 V	< 0.27 μF	N/A	≥ 0.27 µF
1808	ALL	ALL	N/A	N/A
1812	ALL	< 2.2 μF	≥ 2.2 µF	N/A
1825	ALL	ALL	N/A	N/A
2220	ALL	< 10 µF	≥ 10 µF	N/A
2225	ALL	ALL	N/A	N/A

²DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.

³ Capacitance and dissipation factor (DF) measured under the following conditions:

¹ kHz ±50 Hz and 1.0 ±0.2 V_{rms} if capacitance \leq 10 μF

¹²⁰ Hz ± 10 Hz and 0.5 ± 0.1 V $_{\rm rm}$ s if capacitance > 10 μF

⁴To obtain IR limit, divide $M\Omega$ - μ F value by the capacitance and compare to $G\Omega$ limit. Select the lower of the two limits.



Post Environmental Limits

	High Tempe	erature Life, E	Biased Humid	lity, Moisture	Resistance	
Dielectric	Case Size	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance
		< 16		7.5		
	0402	16/25	All	5.0		
		> 25		3.0		
		< 16		7.5		
		16/25	< 1.0 μF	5.0		
	0603	> 25		3.0		
		< 16	≥ 1.0 µF	20.0		
		16/25	2 1.0 μ1	20.0		
		< 16	< 2.2 μF	7.5		
		16/25	ν Ζ.Ζ μι	5.0		
	0805	> 25	< 1.0 µF	3.0		
	0003	< 16	≥ 2.2 µF			
		16/25	ε 2.2 μι	20.0		
X7R		> 25	≥ 1.0 µF		± 20%	10% of Initial
X/K		< 16		7.5	1 20%	limit
		16/25	< 10 µF	5.0		
	1206	> 25		3.0		
	1200	35/50	≥ 2.2 µF			
		< 16	≥ 10 µF	20.0		
		16/25	= 10 μι			
		< 16		7.5		
		16/25	< 22 μF	5.0		
	1210	> 25		3.0		
		< 16	≥ 22 µF	20.0		
		16/25	- 22 μ'			
		< 16		7.5		
	1808-2225	16/25	All	5.0		
		> 25		3.5		



Dissipation Factor (DF) Limit Table

EIA Case Size	Rated DC Voltage	Capacitance	Dissipation Factor (Maximum %)
	< 16	All	5.0
	16	All	3.5
0402	25	< 0.1 µF	3.5
	25	≥ 0.1 µF	10.0
	> 25	All	2.5
	< 16		5.0
	16/25	< 1.0 µF	3.5
0603	> 25		2.5
	< 16	≥ 1.0 µF	10.0
	16/25		
	< 16	< 2.2 μF	5.0
	16/25	·	3.5
0805	> 25	< 1.0 μF	2.5
	< 16	≥ 2.2 µF	
	16/25		10.0
	> 25	≥ 1.0 µF	
	< 16		5.0
	16/25	< 10 μF	3.5
1206	> 25		2.5
1200	35/50	≥ 2.2 µF	10.0
	< 16	≥ 10 µF	10.0
	16/25	_ 10 μ1	
	< 16		5.0
	16/25	< 22 µF	3.5
1210	> 25		2.5
	< 16	≥ 22 µF	10.0
	16/25	- 22 μι	
	< 16		5.0
1808-2225	16/25	All	3.5
	> 25		2.5



Table 1A - Capacitance Range/Selection Waterfall (0402 - 1206 Case Sizes)

			se Si Serie			CO	40	2C				C	06	03	С						CO	080	5C							C1	20	6C			
Сар	Cap	Vol	tage C	ode	9	8	4	3	5	9	8	4	3	5	1	2	A	9	8	4	3	6	5	1	2	A	9	8	4	3	6	5	1	2	A
	Code	Rate	ed Vol (VDC)		6.3	2	16	25	20	6.3	1	16	25	20	100	200	250	6.3	2	16	25	35	20	100	200	250	6.3	2	16	25	35	20	100	200	250
		Сар	Toler						Pro	duct	Ava	ilab	ility	and	Chi	p Th	ickr	ess	Cod	les -	- Se	e Tal	ble 2	2 for	Chi	p Th	ickr	iess	Dim	iens	ions				
10 - 20 pF*	100 - 200*	J	K	М	ВВ		ВВ	ВВ	ВВ	CF	CF	CF	CF	CF	CF	CF						DN		DN			EB								
22 pF 24 - 91pF	220 240 - 910*	J	K	M	BB BB	BB BB	BB BB	BB BB	BB BB	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF		DM DN			DN DN		DN DN	DN DN			EB EB								
100 - 150 pF**	101 - 151**	J	K	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	CF		DN	DN		DN		DN	DN	DN		EB								
180 - 820 pF**		J	K	М	ВВ	ВВ	ВВ	ВВ	ВВ	CF	CF	CF	CF	CF	CF	CF		DN	DN		DN		DN	DN		DN	EB								
1000pF	102	J	K	М	ВВ	ВВ	ВВ	ВВ	ВВ	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB	EB							
1200 pF	122	J	K	М	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN		DN		DN		DN		EB	EB							
1500 pF	152	J	K	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN		DN	DN	DN	DN	DN	DN	EB	EB							
1800 pF 2200 pF	182 222	J	K	M M	BB BB	BB BB	BB BB	BB BB	BB BB	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	DN DN	DN DN	DN DN		DN DN	DN DN		DN DN		EB EB	EB EB							
2700 pF	272	J	K	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN	DN		_	DN	DN	DN		EB	EB							
3300 pF	332	Ĵ	K	М	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN	DN	DN	DN	DN		DN	DN	EB	EB							
3900 pF	392	J	K	М	ВВ	ВВ	ВВ	ВВ	ВВ	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN	DN	DN	DN	DN	DN	DN	DN	EB	ЕВ							
4700 pF	472	J	K	М	ВВ	ВВ	ВВ	ВВ	ВВ	CF	CF	CF	CF	CF	CF	CF	CF	DN			DN		DN		DN	DN	EB	EB							
5600 pF	562	J	K	М	BB	BB	ВВ	ВВ	ВВ	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN		DN		DN	DN	DN	DN	EB	EB							
6800 pF	682	J	K	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	CF	CF	DN	DN		DN		DN	DN	DN	DN	EB	EB							
8200 pF 10000 pF	822 103	J	K	M	BB BB	BB BB	BB BB	BB BB	BB BB	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	CF CF	DN DN	DN DN		DN DN		DN DN	DN DN	DN DN	DN DN	EB EB	EB EB							
12000 pF	123	J	K	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF	UF	UF	DN	DN		DN		DN		DN		EB	EB							
15000 pF	153	Ĵ	K	M	BB	BB	BB	BB	BB	CF	CF	CF	CF	CF	CF			DN	DN	DN		DN	DN		DN	DN	EB	EB							
18000 pF	183	J	K	М	ВВ	ВВ	ВВ	ВВ	BB	CF	CF	CF	CF	CF	CF			DN	DN	DN		_	DN	DN	DN		EB	EB							
22000 pF	223	J	K	М	BB	BB	ВВ	ВВ	BB	CF	CF	CF	CF	CF	CF			DN	DN	DN	DN	DN	DN	DN	DN	DN	EB	EB							
27000 pF	273	J	K	М	ВВ	BB	BB	BB		CF	CF	CF	CF	CF	CF			DN	DN	DN			DN	DP	DE		EB	EB							
33000 pF	333	J	K	M	BB	BB	BB	BB		CF	CF	CF	CF	CF	CF			DN	DN		DN	DN	DN	DP	DE	DG	EB	EB							
39000 pF 47000 pF	393 473	J	K	M	BB BB	BB BB	BB BB	BB BB		CF	CF CF	CF CF	CF CF	CF CJ	CF CF			DN DO	DN DO	DN DO	DN DO	DN DO	DN DO	DP DE	DE DG	DG DG	EB EB	EB EB	EB EB	EB EB	EB EB	EB EB	EC EC	EB ED	EB ED
56000 pF	563	J	K	M	BB	BB	ВВ	ВВ		CF	CF	CF	CF	CF	UF			DP	DP	DP	DP	DP	DP	DE	DG		EB	ED	ED						
68000 pF	683	Ĵ	K	М	BB	BB	BB			CF	CF	CF	CF	CF				DP	DP	DP	DP.	DP	DP	DE	DG		EB	ED	ED						
82000 pF	823	J	K	М	ВВ	ВВ	ВВ			CF	CF	CF	CF	CF				DP	DP	DP	DP	DP	DP	DE			EB	ED	ED						
0.1 μF	104	J	K	М	ВВ	ВВ	ВВ	BB1		CJ	CJ	CJ	CJ	CJ				DN	DN	DN	DN	DN	DN	DE			EB	EM	ЕМ						
0.12 μF	124	J	K	М						CF	CF	CF	CF	CF				DN	DN	DN	DN	DP	DP	DG			EC	EG	EM						
0.15 μF	154	J	K	M						CF	CF	CF	CF	CF				DN	DN	DN	DN	DP	DP	DG			EC	EG	EG						
0.18 µF	184 224	J	K	M						CF CF	CF CF	CF CF	CF CF					DN DN	DN DN	DN DN	DN DN	DG DG	DG DG	DG DG			EC EC	EM EG	EM EG						
0.22 μF 0.27 μF	274	J	K	M						CF	CF	CF	GF					DP	DP	DP	DP	DP	DP	טט			EB	EB	EB	EB	EC	EC	EM	EG	EG
0.27 μF	334	Ĵ	K	M						CF	CF	CF						DG	DG	DG	DG	DP	DP				EB	EB	EB	EB	EC	EC	EG		
0.39 µF	394	Ĵ	K	М	l					CF	CF	CF						DG	DG	DG			DE				EB	EB	EB	EB	EC	EC	EG		
0.47 μF	474	J	K	М						CF	CF	CF	CG1					DG	DG		DG	DE	DE				EC	EC	EC	EC	EC	EC	EG		I
0.56 μF	564	J	K	М														DP	DP	DP	DG	DH	DH				ED	ED	ED	ED	EC	EC	EM		
0.68 µF	684	J	K	M														DP	DP	DP	DG	DH	DH				EE	EE	EE	EE	ED	ED	EM		
0.82 μF 1 μF	824 105	J	K	M						CG ¹	CG1	CG1	CD1					DP np	DP np		DG	DG¹	DG1				EF EP	EF EP	EF EP	EF EP	ED ED	ED	EH		
1 μF 1.2 μF	125	J	K	M						00.	00	00.	OD.						DE		טע	DG.	DG.				ED	ED			EH		LII		
1.5 µF	155	Ĵ	K	M															DG								ED	ED	ED		EH				
1.8 μF	185	J	K	М														DG	DG	DG							ED	ED	ED	EF	EH	EH			
2.2 µF	225	J	K	М						CG1	CG1							DG	DG	DG	DG ¹						EH		1		EH	EH			
2.7 μF	275	J	K	М																							EN	EN		EH					
3.3 µF	335	J	K	M																							ED EF	ED	ED EF	EH					
3.9 μF 4.7 μF	395 475	J J	K	M														DG	DG	DG							EH				EH1	FH1			
рі	···		ed Vol	tage	6.3	2	9	25	20	6.3	10	16	25	20	100	200	250	6.3	2	16	25	35	20	100	200	250	6.3	2::	9	25		20	100	200	250
0	 Cap		(VDC)		⊢	_										_	_	\vdash		_					_	-	┢	-				_		$\overline{}$	
Сар	Code		tage C		9	8	4	3	5	9	8	4	3	5	1	2	A	9	8	4	3	6	5	1	2	Α	9	8	4	3		5	1	2	A
			Serie				0402	2C					C06	03C							C	0805	C —							C	1206	C			

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91).

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68, and 82).

 xx^1 Available only in K and M tolerance.



Table 1A - Capacitance Range/Selection Waterfall (0402 - 1206 Case Sizes) cont'd

		Case	e Si erie			CO	40	2C				C	:06	03(C						CO	80	5C							C1	20	6C			
Сар	Сар	Volta	ge C	ode	9	8	4	3	5	9	8	4	3	5	1	2	Α	9	8	4	3	6	5	1	2	Α	9	8	4	3	6	5	1	2	Α
oup	Code	Rated (\	Vol /DC)		6.3	10	16	25	20	6.3	10	16	25	20	100	200	250	6.3	2	16	25	35	20	100	200	250	6.3	10	16	25	35	20	100	200	250
		Cap To	olera	ance					Pro	duct	Ava	ilab	ility	and	Chi	p Th	ickn	ess	Cod	les -	- Se	e Tal	ble 2	2 for	Chi	p Th	ickr	iess	Dim	ens	ions				
5.6 µF	565	J	K	М																							EH	EH	EH						
6.8 µF	685	J	K	M																							EH	EH	EH						
8.2 μF	825	J	K	M																							EH	EH	EH						
10 μF	106	J	K	M														DH	DH								EH	EH	EH	EH					
22 μF	226	J	K	М																							EH1	EH1							
		Rated (\	Vol /DC)		6.3	10	16	25	20	6.3	10	16	25	20	100	200	250	6.3	1	16	25	35	20	100	200	250	6.3	1	16	25	35	20	100	200	250
Сар	Cap Code	Volta	ge C	ode	9	8	4	3	5	9	8	4	3	5	1	2	A	9	8	4	3	6	5	1	2	A	9	8	4	3	6	5	1	2	Α
	Joue		ise Size/ Series	C	0402	2C					C06	03C							C	0805	C	-		•				C	1206	iC.					

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91).

Table 1B - Capacitance Range/Selection Waterfall (1210 - 2225 Case Sizes)

	Cap		se Si Serie				(C12	100	;			C1	808	BC		C1	812	2C		(C18	250	2		C2	22	0C		(222	250)
Cap		Vol	tage C	ode	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	Α	5	1	2	Α	3	5	1	2	Α	5	1	2	A
	Code	Rat	ed Volt (VDC)		6.3	10	16	25	20	100	200	250	09	100	200	25	20	100	200	250	20	100	200	250	25	20	100	200	250	50	100	200	250
		Cap	Tolera	ance				Pr	oduc	t Av	aila	bilit	y and	d Ch	ip T	hickı	ness	Cod	les -	- Se	e Tal	ole 2	for	Chip	Thi	ckne	ess I	Dime	nsio	ns			
10 - 91 pF*	100 - 910*	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
11 pF	110	J	K	M	FB	FB	FB	FB	FB	FB	FB																			l			
12 pF	120	J	K	М	FB	FB	FB	FB	FB	FB	FB																			l			
13 pF	130	J	K	М	FB	FB	FB	FB	FB	FB	FB																			l			
15 pF	150	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ														İ			
16 pF	160	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
18 pF	180	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ					l				İ					İ			
20 pF	200	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ					İ				İ					İ			
22 pF	220	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ					İ				İ					İ			
24 pF	240	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ					İ				İ					İ			
27 pF	270	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
30 pF	300	J	K	М	FB	FB	FB	FB	FB	FB	FB																			İ			
33 pF	330	J	K	М	FB	FB	FB	FB	FB	FB	FB																			İ			
36 pF	360	J	K	М	FB	FB	FB	FB	FB	FB	FB																			İ			
39 pF	390	J	K	М	FB	FB	FB	FB	FB	FB	FB																			İ			
43 pF	430	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
47 pF	470	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ					İ				İ					İ			
51 pF	510	J	K	М	FB	FB	FB	FB	FB	FB	FB					l					l				ĺ					İ			
56 pF	560	J	K	М	FB	FB	FB	FB	FB	FB	FB					l					l				ĺ					İ			
62 pF	620	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ					İ				İ					İ			
68 pF	680	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
75 pF	750	J	K	М	FB	FB	FB	FB	FB	FB	FB					İ														İ			
	Con	Rat	K M F K M F K M F ed Voltage (VDC)		6.3	9	16	25	20	100	200	250	20	100	200	25	20	100	200	250	20	100	200	250	25	20	100	200	250	20	100	200	250
Cap	Cap Code	Vol	tage C	ge Code		8	4	3	5	1	2	A	5	1	2	3	5	1	2	Α	5	1	2	Α	3	5	1	2	Α	5	1	2	A
			se Siz Series					C12	10C				C.	1808	C		С	1812	2C			C18	25C			C	2220	С			C22	25C	

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91).

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68, and 82).

 xx^1 Available only in K and M tolerance.

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68, and 82).

xx¹ Available only in K and M tolerance.



Table 1B - Capacitance Range/Selection Waterfall (1210 - 2225 Case Sizes) cont'd

			se Si Serie				(C12	100	.			C1	808	8C		C1	812	2C		(C18	250	C		C2	222	0C		(222	25(;
Сар	Cap	Vol	tage C	ode	9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	Α	5	1	2	Α	3	5	1	2	Α	5	1	2	Α
	Code	Rate	ed Volt (VDC)	-	6.3	2	16	25	20	100	200	250	20	100	200	25	20	100	200	250	20	100	200	250	25	20	100	200	250	20	9	200	250
		Сар	Tolera	ance				Pr	odu	t Av	aila	bilit	y an	d Ch	ip Tl	hickı	ıess	Cod	les -	- See	e Tal	ole 2	for	Chip	Thi	ckne	ess I	Dime	ensio	ns			
82 pF	820	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
91 pF	910	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
100 - 270 pF**	101 - 271**	J	K	M	FB	FB	FB	FB	FB	FB	FB																						
110 pF	111	J	K	M	FB	FB	FB	FB	FB	FB FB	FB FB					ŀ														l			
120 pF 130 pF	121 131	J	K	M	FB FB	FB FB	FB FB	FB FB	FB FB	FB	FB																						
150 pF	151	J	K	M	FB	FB	FB	FB	FB	FB	FB					l														l			
180 pF	181	Ĵ	K	M	FB	FB	FB	FB	FB	FB	FB					l									İ					l			
220 pF	221	J	K	М	FB	FB	FB	FB	FB	FB	FB																			İ			
270 pF	271	J	K	М	FB	FB	FB	FB	FB	FB	FB																						
330 pF	331	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF																		
390 pF	391	J	K	М	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF																		
470 - 1,200 pF**	471 - 122**	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB														
560 pF	561	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB		1												
680 pF 820 pF	681 821	J	K	M	FB FB	FB FB	FB FB	FB FB	FB FB	FB FB	FB FB		LF LF	LF LF	LF LF	GB GB	GB GB	GB GB	GB GB														
1,000 pF	102	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB														
1,200 pF	122	J	K	M	FB	FB	FB	FB	FB	FB	FB		LF	LF	LF	GB	GB	GB	GB						l					l			
1,500 pF	152	Ĵ	K	M	FB	FB	FB	FB	FB	FB	FE		LF	LF	LF	GB	GB	GB	GB														
1,800 pF	182	J	K	М	FB	FB	FB	FB	FB	FB	FE		LF	LF	LF	GB	GB	GB	GB											İ			
2,200 pF	222	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF	LF	GB	GB	GB	GB											l			
2,700 pF	272	J	K	М	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF	LF	GB	GB	GB	GB														
3,300 pF	332	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF		GB	GB	GB	GB														
3,900 pF	392	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LF	LF		GB	GB	GB	GB		НВ	НВ	HB							l			
4,700 pF	472	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD	LD	GB	GB	GB	GD		НВ	НВ	НВ							KE	KE	KE	
5,600 pF 6,800 pF	562 682	J	K	M	FB FB	FB FB	FB FB	FB FB	FB FB	FB FB	FB FB	FB FB	LD LD	LD LD	LD LD	GB GB	GB GB	GB GB	GH GB	GB	HB HB	HB HB	HB HB		JE	JE	JE			KE KE	KE KE	KE KE	
8,200 pF	822	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD	LD	GB	GB	GB	GB		НВ	НВ	НВ		JE	JE	JE			KE	KE	KE	
10,000 pF	103	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD	LD	GB	GB	GB	GB		НВ	НВ	HE		JE	JE	JE			KE	KE	KE	
12,000 pF	123	Ĵ	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD	LD	GB	GB	GB	GB	GB		НВ	HE		JE	JE	JE			KE	KE	KE	
15,000 pF	153	J	K	М	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD	LD	GB	GB	GB	GB		НВ	НВ			JE	JE	JE			KE	KE	KE	
18,000 pF	183	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD	LD	GB	GB	GB	GB	GB	НВ	HE			JE	JE	JE			KE	KE		
22,000 pF	223	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB	GB	НВ	НВ		НВ	JE	JE	JE			KE	KE		
27,000 pF	273	J	K	М	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB		НВ	НВ	НВ	НВ	JE	JE	JE			KE	KE		
33,000 pF	333	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB		НВ	НВ	НВ	НВ	JB	JB	JB			KE			
39,000 pF	393	J	K	M	FB	FB	FB	FB	FB	FB	FB	FB	LD	LD		GB	GB	GB	GB		НВ	НВ	НВ	НВ	JB	JB	JB						
47,000 pF 56,000 pF	473 563	J	K	M	FB FB	FB FB	FB FB	FB FB	FB FB	FB FB	FC FC	FC FC	LD LD	LD LD		GB GB	GB GB	GB GB	GB GB	GB GB	HB HB	HB HB	HB HB	HB HB	JB JB	JB JB	JB JB						
68,000 pF	683	J	K	M	FB	FB	FB	FB	FB	FB	FC	_	LD	רח		GB	GB	GB		GB	_	НВ	НВ	НВ	JB	JB	JB						
82,000 pF	823	J	K	M	FB	FB	FB	FB	FB	FC	FF	FF	LD			GB				GB		НВ		НВ		JC	JC	JC	JC				
0.10 μF	104	Ĵ	K	M	FB	FB	FB	FB	FB	FD	FG	FG	LD			GB	GB	GB	GB	GB	НВ	НВ	НВ	НВ	JC	JC	JC	JC	JC	кс	KC	KC	KC
0.12 μF	124	J	K	M	FB	FB	FB	FB	FB	FD	FH	FH				GB	GB	GB	GB	GB		НВ	НВ	НВ	JC	JC	JC	JC	JC	KC			KC
0.15 μF	154	J	K	М	FC	FC	FC	FC	FC	FD	FM	FM	LD			GB	GB	GB	GE			НВ	НВ	НВ	JC	JC	JC	JC	JC	KC	KC	KC	KC
0.18 μF	184	J	K	М	FC	FC	FC	FC	FC	FD	FK	FK	LD			GB	GB	GB					НВ	НВ	JC	JC	JC	JC	JC	KC	KC		KC
0.22 μF	224	J	K	M	FC	FC	FC	FC	FC	FD	FK					GB	GB	GB				НВ	НВ	НВ	JC	JC	JC	JC	JC	KC	1 1	1 1	KC
0.27 µF	274	J	K	M	FC	FC	FC	FC	FC	FD	FP	FP				GB	GB	GG	GG			НВ	НВ	НВ	JC	JC	JC	JC	JC	KB	KC		KC
0.33 μF 0.39 μF	334	J	K	M	FD	FD FD	FD FD	FD FD	FD FD	FD FD	FK	FM FK				GB	GB GB	GG GG	GG GG			НВ	HB	HB	JC JC	JC JC	JC JC	JC JC	JC	KB KB		1 1	KC
0.39 μF 0.47 μF	394 474	,l	K	M	FD FD	_		FD	FD	FD	FS	FS				GB GB	GB	GG	GJ			НВ		HD HD	JC	JC	JC	JC	JC	KB	KC		KC KD
μι			ed Volt	tage	6.3	2	9	25	20	100	200	250	20	100	200	25	20	100	200	250	20	100	200	250	25	20	100	200	250	20	100	200	250
Сар	Сар	-	(VDC) tage C		9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	7 A	5	1	2	A	3	5	1	2	7 A	5	1	2	7 A
- Cup	Code	Ca	se Siz	ze/					10C		_			1808		Ť		1812				C18					2220			\vdash	C22		-
			Series	S									بَـــا								$ldsymbol{ld}}}}}}$							-					

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91).

 xx^1 Available only in K and M tolerance.

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68, and 82).



Table 1B - Capacitance Range/Selection Waterfall (1210 - 2225 Case Sizes) cont'd

	Con		se Si Serie				(C12	100	C			C 1	80	8C		C	181	2C			C18	250	C		C2	222	0C		(22	250	3
Cap	Cap	Vol	ltage C	ode	9	8	4	3	5	1	2	A	5	1	2	3	5	1	2	A	5	1	2	A	3	5	1	2	A	5	1	2	Α
·	Code	Rat	ed Vol		6.3	10	16	25	20	100	200	250	20	100	200	25	20	100	200	250	20	100	200	250	25	20	100	200	250	20	100	200	250
		Сар	Tolera	ance				Pr	odu	ct Av	aila	bilit	y an	d Ch	ip T	hick	ness	Co	des	– Se	e Ta	ble 2	for	Chip	Thi	ckne	ess	Dime	nsio	ons			
0.56 μF	564	J	K	М	FD	FD	FD	FD	FD	FF						GC	GC	GG			НВ	HD	HD	HD	JC	JC	JC	JD	JD	KB	KC	KD	KD
0.68 μF	684	J	K	M	FD	FD	FD	FD	FD	FG						GC	GC				НВ	HD	HD	HD	JC	JC	JD	JD	JD	KB	KC	KD	KD
0.82 μF	824	J	K	M	FF	FF	FF	FF	FF	FL						GE	GE				НВ	HF	HF		JC	JC	JF	JF	JF	KB	KC	KE	KE
1.0 μF	105	J	K	M	FH	FH	FH	FH	FH							GE	GE				НВ	HF	HF	HF	JC	JC	JF	JF	JF	KB	KD	KE	KE
1.2 μF	125	J	K	M	FH	FH		FH	FG	FH						GB	GB				НВ				JC	JC				KB	KE	KE	KE
1.5 μF	155	J	K	M	FH	FH	FH		FG	FM						GC	GC				HC				JC	JC				KC			
1.8 μF	185	J	K	M	FH	FH		FH	FG	FJ			l			GE	GE				HD				JD	JD				KD			
2.2 μF	225	J	K	M	FJ	FJ	FJ	FJ		FT1			l			G0		GO1	1		HF				JF	JF				KD			
2.7 μF	275	J	K	M	FE	FE	FE	FG	FH							GJ	GJ	GJ															
3.3 μF	335	J	K	M	FF	FF	FF	FM								GL	GL	GL															
3.9 µF	395	J	K	M	FG	FG	FG	FG	FK							l																	
4.7 μF	475	J	K	M	FC	FC	FC	FG	FS							GK	GK								JF	JF							
5.6 μF	565	J	K	M	FF	FF	FF	FH																						l			
6.8 μF	685	J	K	M	FG	FG	FG	FM																						l			
8.2 μF	825	J	K	М	FH	FH	FH	FK																									
10 μF	106	J	K	M	FT1	FT1	FT1	FS ¹	FS1				l			GK					l				JF	JO				l			
12 μF	126	J	K	М	Ī								İ			İ					İ				İ					l			
15 μF	156	J	K	М	FM	FM							İ			İ					İ				JO	JO				l			
18 μF	186	J	K	М	Ī								İ			İ					İ				İ					l			
22 µF	226	J	K	М	FS	FS	FS ¹	FS ¹																	JO					İ			
47 μF	476	J	K	М	FS ¹	FS ¹																											
	_	Rat	K M F		6.3	10	16	25	20	100	200	250	50	100	200	25	50	100	200	250	50	100	200	250	25	50	100	200	250	50	100	200	250
Cap	Cap Code	Vo	` ′		9	8	4	3	5	1	2	Α	5	1	2	3	5	1	2	A	5	1	2	Α	3	5	1	2	Α	5	1	2	Α
	Coue		se Si Series					C12	10C			,	С	1808	3C		С	1812	2C			C18	25C			C	222	0C			C22	25C	

^{*}Capacitance range Includes E24 decade values only. (i.e., 10, 11, 12, 13, 15, 16, 18, 20, 22, 24, 27, 30, 33, 36, 39, 43, 47, 51, 56, 62, 68, 75, 82, and 91).

^{**}Capacitance range Includes E12 decade values only. (i.e., 10, 12, 15, 18, 22, 27, 33, 39, 47, 56, 68, and 82).

 xx^1 Available only in K and M tolerance.



Table 2A - Chip Thickness/Tape & Reel Packaging Quantities

	•		•	1	DI 1' 0 1'					
Thickness	Case	Thickness ±	Paper Q	uantity ¹	Plastic (Quantity				
Code	Size ¹	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel				
ВВ	0402	0.50 ±0.05	10,000	50,000	0	0				
CF	0603	0.80 ±0.07*	4,000	15,000	0	0				
CG	0603	0.80 ±0.10*	4,000	15,000	0	0				
CD	0603	0.80 ±0.15	4,000	10,000	0	0				
CJ	0603	0.80 ±0.15*	4,000	15,000	0	0				
DM	0805	0.70 ±0.20*	4,000	15,000	0	0				
DN DO	0805 0805	0.78 ±0.10* 0.80 ±0.10*	4,000	15,000 15,000	0	0 0				
DD DP	0805	0.80 ±0.10* 0.90 ±0.10*	4,000 4,000	15,000	0 0	0				
DE	0805	1.00 ±0.10	4,000	0	2,500	10,000				
DG	0805	1.25 ±0.15	0	0	2,500	10,000				
DH	0805	1.25 ±0.10	Ö	Ö	2,500	10,000				
EB	1206	0.78 ±0.10	4,000	10,000	4,000	10,000				
EC	1206	0.90 ±0.10	0	0	4,000	10,000				
EN	1206	0.95 ±0.10	0	0	4,000	10,000				
ED	1206	1.00 ±0.10	0	0	2,500	10,000				
EE	1206	1.10 ±0.10	0	0	2,500	10,000				
EF	1206	1.20 ±0.15	0	0	2,500	10,000				
EP	1206	1.20 ±0.20	0	0	2,500	10,000				
EM	1206	1.25 ±0.15	0	0	2,500	10,000				
EG	1206	1.60 ±0.15	0	0	2,000	8,000				
EH	1206	1.60 ±0.20	0	0	2,000	8,000				
FB	1210	0.78 ±0.10	0	0	4,000	10,000				
FC	1210	0.90 ±0.10	0	0	4,000	10,000				
FD	1210	0.95 ±0.10	0	0	4,000	10,000				
FE	1210	1.00 ±0.10	0	0	2,500	10,000				
FF	1210	1.10 ±0.10	0	0	2,500	10,000				
FG	1210	1.25 ±0.15	0	0	2,500	10,000				
FL FH	1210 1210	1.40 ±0.15	0	0	2,000	8,000				
FP FP	1210	1.55 ±0.15 1.60 ±0.20	0	0	2,000 2,000	8,000 8,000				
FM	1210	1.70 ±0.20	0	0	2,000	8,000				
FJ	1210	1.85 ±0.20	0	0	2,000	8,000				
FT	1210	1.90 ±0.20	0	0	2,000	8,000				
FK	1210	2.10 ±0.20	0	0	2,000	8,000				
FS	1210	2.50 ±0.30	0	0	1,000	4,000				
NA	1706	0.90 ±0.10	0	0	4,000	10,000				
NC	1706	1.00 ±0.15	0	0	4,000	10,000				
LD	1808	0.90 ±0.10	0	0	2,500	10,000				
LF	1808	1.00 ±0.15	0	0	2,500	10,000				
GB	1812	1.00 ±0.10	0	0	1,000	4,000				
GC	1812	1.10 ±0.10	0	0	1,000	4,000				
GD	1812	1.25 ±0.15	0	0	1,000	4,000				
GE	1812	1.30 ±0.10	0	0	1,000	4,000				
GH	1812	1.40 ±0.15	0	0	1,000	4,000				
GG	1812	1.55 ±0.10	0	0	1,000	4,000				
GK	1812	1.60 ±0.20	0	0	1,000	4,000				
GJ	1812	1.70 ±0.15	0	0	1,000	4,000				
GL GO	1812	1.90 ±0.20	0	0 0	500 500	2,000				
	1812	2.50 ±0.20	0 7" Pool		500	2,000				
Thickness Code	Case Size ¹	Thickness ± Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel				
Code	3126	Range (IIIII)	Paper Q	uantity1	Plastic (Quantity				

Package quantity based on finished chip thickness specifications.

¹ If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information."



Table 2A - Chip Thickness/Tape & Reel Packaging Quantities cont'd

Thickness	Case	Thickness ±	Paper Q	uantity ¹	Plastic Quantity		
Code	Size ¹	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel	
НВ	1825	1.10 ±0.15	0	0	1,000	4,000	
HC	1825	1.15 ±0.15	0	0	1,000	4,000	
HD	1825	1.30 ±0.15	0	0	1,000	4,000	
HE	1825	1.40 ±0.15	0	0	1,000	4,000	
HF	1825	1.50 ±0.15	0	0	1,000	4,000	
JB	2220	1.00 ±0.15	0	0	1,000	4,000	
JC	2220	1.10 ±0.15	0	0	1,000	4,000	
JD	2220	1.30 ±0.15	0	0	1,000	4,000	
JE	2220	1.40 ±0.15	0	0	1,000	4,000	
JF	2220	1.50 ±0.15	0	0	1,000	4,000	
J0	2220	2.40 ±0.15	0	0	500	2,000	
KB	2225	1.00 ±0.15	0	0	1,000	4,000	
KC	2225	1.10 ±0.15	0	0	1,000	4,000	
KD	2225	1.30 ±0.15	0	0	1,000	4,000	
KE	2225	1.40 ±0.15	0	0	1,000	4,000	
Thickness	Case	Thickness ±	7" Reel	13" Reel	7" Reel	13" Reel	
Code	Size ¹	Range (mm)			Plastic Quantity		

Package quantity based on finished chip thickness specifications.

Table 2B - Bulk Packaging Quantities

Dookoai	ng Tuno	Loose P	Loose Packaging				
Packagi	ng Type	Bulk Bag (default)					
Packagin	g C-Spec¹	N,	/A ²				
Case	Size	Packaging Quantities (pieces/unit packaging)				
EIA (in)	Metric (mm)	Minimum	Maximum				
0402	1005						
0603	1608						
0805	2012		50,000				
1206	3216						
1210	3225	1					
1808	4520] '					
1812	4532						
1825	4564		20,000				
2220	5650						
2225	5664						

¹ The "Packaging C-Spec" is a 4 to 8 digit code which identifies the packaging type and/or product grade. When ordering, the proper code must be included in the 15th through 22nd character positions of the ordering code. See "Ordering Information" section of this document for further details. Commercial grade product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging. Contact KEMET if you require a bulk bag packaging option for automotive grade products.

¹ If ordering using the 2 mm Tape and Reel pitch option, the packaging quantity outlined in the table above will be doubled. This option is limited to EIA 0603 (1608 metric) case size devices. For more information regarding 2 mm pitch option see "Tape & Reel Packaging Information."

² A packaging C-Spec (see note 1 above) is not required for "Bulk Bag" packaging (excluding anti-static Bulk Bag and automotive grade products). The 15th through 22nd character positions of the ordering code should be left blank. All product ordered without a packaging C-Spec will default to our standard "Bulk Bag" packaging.



Table 3 - Chip Capacitor Land Pattern Design Recommendations per IPC-7351


EIA Size Code	Metric Size Code	Density Level A: Maximum (Most) Land Protrusion (mm)				Density Level B: Median (Nominal) Land Protrusion (mm)				Density Level C: Minimum (Least) Land Protrusion (mm)						
		С	Y	X	V1	V2	С	Y	X	V1	V2	С	Υ	X	V1	V2
0402	1005	0.50	0.72	0.72	2.20	1.20	0.45	0.62	0.62	1.90	1.00	0.40	0.52	0.52	1.60	0.80
0603	1608	0.90	1.15	1.10	4.00	2.10	0.80	0.95	1.00	3.10	1.50	0.60	0.75	0.90	2.40	1.20
0805	2012	1.00	1.35	1.55	4.40	2.60	0.90	1.15	1.45	3.50	2.00	0.75	0.95	1.35	2.80	1.70
1206	3216	1.60	1.35	1.90	5.60	2.90	1.50	1.15	1.80	4.70	2.30	1.40	0.95	1.70	4.00	2.00
1210	3225	1.60	1.35	2.80	5.65	3.80	1.50	1.15	2.70	4.70	3.20	1.40	0.95	2.60	4.00	2.90
1210¹	3225	1.50	1.60	2.90	5.60	3.90	1.40	1.40	2.80	4.70	3.30	1.30	1.20	2.70	4.00	3.00
1808	4520	2.30	1.75	2.30	7.40	3.30	2.20	1.55	2.20	6.50	2.70	2.10	1.35	2.10	5.80	2.40
1812	4532	2.15	1.60	3.60	6.90	4.60	2.05	1.40	3.50	6.00	4.00	1.95	1.20	3.40	5.30	3.70
1825	4564	2.15	1.60	6.90	6.90	7.90	2.05	1.40	6.80	6.00	7.30	1.95	1.20	6.70	5.30	7.00
2220	5650	2.75	1.70	5.50	8.20	6.50	2.65	1.50	5.40	7.30	5.90	2.55	1.30	5.30	6.60	5.60
2225	5664	2.70	1.70	6.90	8.10	7.90	2.60	1.50	6.80	7.20	7.30	2.50	1.30	6.70	6.50	7.00

¹ Only for capacitance values ≥ 22 μF

Density Level A: For low-density product applications. Recommended for wave solder applications and provides a wider process window for reflow solder processes. KEMET only recommends wave soldering of EIA 0603, 0805, and 1206 case sizes.

Density Level B: For products with a moderate level of component density. Provides a robust solder attachment condition for reflow solder processes. Density Level C: For high component density product applications. Before adapting the minimum land pattern variations the user should perform qualification testing based on the conditions outlined in IPC Standard 7351 (IPC-7351).

Image below based on Density Level B for an EIA 1210 case size.





Soldering Process

Recommended Soldering Technique:

- Solder wave or solder reflow for EIA case sizes 0603, 0805 and 1206
- · All other EIA case sizes are limited to solder reflow only

Recommended Reflow Soldering Profile:

KEMET's families of surface mount multilayer ceramic capacitors (SMD MLCCs) are compatible with wave (single or dual), convection, IR or vapor phase reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for convection and IR reflow reflect the profile conditions of the IPC/ J-STD-020 standard for moisture sensitivity testing. These devices can safely withstand a maximum of three reflow passes at these conditions.

	Torminati	Termination Finish					
Profile Feature	Terminati						
	SnPb	100% Matte Sn					
Preheat/Soak							
Temperature Minimum (T _{Smin})	100°C	150°C					
Temperature Maximum (T _{Smax})	150°C	200°C					
Time (t_s) from T_{smin} to T_{smax}	60 - 120 seconds	60 - 120 seconds					
Ramp-Up Rate $(T_L \text{ to } T_p)$	3°C/second maximum	3°C/second maximum					
Liquidous Temperature (T_L)	183°C	217°C					
Time Above Liquidous (t _L)	60 - 150 seconds	60 - 150 seconds					
Peak Temperature (T _P)	235°C	260°C					
Time Within 5°C of Maximum Peak Temperature (t _p)	20 seconds maximum	30 seconds maximum					
Ramp-Down Rate (T _P to T _L)	6°C/second maximum	6°C/second maximum					
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum					

Note 1: All temperatures refer to the center of the package, measured on the capacitor body surface that is facing up during assembly reflow.






Table 4 - Performance & Reliability: Test Methods and Conditions


Stress	Reference		Test or Inspection Mo	ethod					
Terminal Strength	JIS-C-6429	Appendix 1, Note: Force of 1	.8 kg for 60 seconds.						
Board Flex	JIS-C-6429	Appendix 2, Note: Standard termination system – 2.0 mm (minimum) for all except 3 mm for COG. Flexible termination system – 3.0 mm (minimum).							
		Magnification 50 X. Condition	ns:						
Caldanahilitu	L OTD OOG	a) Method B, 4 hours a	t 155°C, dry heat at 235°C						
Solderability	J-STD-002	b) Method B, category	3 at 215°C						
		c) Method D, category	3 at 260°C						
Temperature Cycling	JESD22 Method JA-104	1,000 Cycles (-55°C to +125	°C). Measurement at 24 hou	ırs ±4 hours after test conclusion.					
Biased Humidity	MIL-STD-202 Method 103	Load Humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100 K ohm resistor. Measurement at 24 hours ±4 hours after test conclusion. Low Volt Humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor. Measurement at 24 hours ±4 hours after test conclusion.							
Moisture Resistance	MIL-STD-202 Method 106	t = 24 hours/cycle. Steps 7a and 7b not required. Measurement at 24 hours ±4 hours after test conclusion.							
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Numbe seconds. Dwell time - 15 mi		Maximum transfer time – 20					
		1,000 hours at 125°C with 2 X rated voltage applied excluding the following:							
_	MIL-STD-202	Case Size	Capacitance	Applied Voltage					
High Temperature Life	Method 108/EIA-198	0603 & 0805	≥ 1.0 µF	1.5 X					
		1206 & 1210	≥ 10 µF	1.5 A					
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC for 1,000 hours	S.						
Vibration	MIL-STD-202 Method 204	5 g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz							
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Con	Figure 1 of Method 213, Condition F.						
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical	, OKEM Clean or equivalent						

Storage & Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature – reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction (Typical)





Capacitor Marking (Optional):

These surface mount multilayer ceramic capacitors are normally supplied unmarked. If required, they can be marked as an extra cost option. Marking is available on most KEMET devices, but must be requested using the correct ordering code identifier(s). If this option is requested, two sides of the ceramic body will be laser marked with a "K" to identify KEMET, followed by two characters (per EIA-198 - see table below) to identify the capacitance value. EIA 0603 case size devices are limited to the "K" character only.

Laser marking option is <u>not</u> available on:

- COG, ultra stable X8R and Y5V dielectric devices.
- EIA 0402 case size devices.
- EIA 0603 case size devices with flexible termination option.
- KPS commercial and automotive grade stacked
- X7R dielectric products in capacitance values outlined below.

EIA Case Size	Metric Size Code	Capacitance
0603	1608	≤ 170 pF
0805	2012	≤ 150 pF
1206	3216	≤ 910 pF
1210	3225	≤ 2,000 pF
1808	4520	≤ 3,900 pF
1812	4532	≤ 6,700 pF
1825	4564	≤ 0.018 µF
2220	5650	≤ 0.027 µF
2225	5664	≤ 0.033 µF

Marking appears in legible contrast. Illustrated below is an example of an MLCC with laser marking of "KA8", which designates a KEMET device with rated capacitance of 100 µF. Orientation of marking is vendor optional.





Capacitor Marking (Optional) cont'd

	Capacitance (pF) For Various Alpha/Numeral Identifiers											
Almha						Numera	ıl					
Alpha Character	9	0	1	2	3	4	5	6	7	8		
Cilaracter	Capacitance (pF)											
Α	0.10	1.0	10	100	1,000	10,000	100,000	1,000,000	10,000,000	100,000,000		
В	0.11	1.1	11	110	1,100	11,000	110,000	1,100,000	11,000,000	110,000,000		
С	0.12	1.2	12	120	1,200	12,000	120,000	1,200,000	12,000,000	120,000,000		
D	0.13	1.3	13	130	1,300	13,000	130,000	1,300,000	13,000,000	130,000,000		
Е	0.15	1.5	15	150	1,500	15,000	150,000	1,500,000	15,000,000	150,000,000		
F	0.16	1.6	16	160	1,600	16,000	160,000	1,600,000	16,000,000	160,000,000		
G	0.18	1.8	18	180	1,800	18,000	180,000	1,800,000	18,000,000	180,000,000		
Н	0.20	2.0	20	200	2,000	20,000	200,000	2,000,000	20,000,000	200,000,000		
J	0.22	2.2	22	220	2,200	22,000	220,000	2,200,000	22,000,000	220,000,000		
K	0.24	2.4	24	240	2,400	24,000	240,000	2,400,000	24,000,000	240,000,000		
L	0.27	2.7	27	270	2,700	27,000	270,000	2,700,000	27,000,000	270,000,000		
М	0.30	3.0	30	300	3,000	30,000	300,000	3,000,000	30,000,000	300,000,000		
N	0.33	3.3	33	330	3,300	33,000	330,000	3,300,000	33,000,000	330,000,000		
Р	0.36	3.6	36	360	3,600	36,000	360,000	3,600,000	36,000,000	360,000,000		
Q	0.39	3.9	39	390	3,900	39,000	390,000	3,900,000	39,000,000	390,000,000		
R	0.43	4.3	43	430	4,300	43,000	430,000	4,300,000	43,000,000	430,000,000		
S	0.47	4.7	47	470	4,700	47,000	470,000	4,700,000	47,000,000	470,000,000		
Т	0.51	5.1	51	510	5,100	51,000	510,000	5,100,000	51,000,000	510,000,000		
U	0.56	5.6	56	560	5,600	56,000	560,000	5,600,000	56,000,000	560,000,000		
V	0.62	6.2	62	620	6,200	62,000	620,000	6,200,000	62,000,000	620,000,000		
W	0.68	6.8	68	680	6,800	68,000	680,000	6,800,000	68,000,000	680,000,000		
Х	0.75	7.5	75	750	7,500	75,000	750,000	7,500,000	75,000,000	750,000,000		
Υ	0.82	8.2	82	820	8,200	82,000	820,000	8,200,000	82,000,000	820,000,000		
Z	0.91	9.1	91	910	9,100	91,000	910,000	9,100,000	91,000,000	910,000,000		
а	0.25	2.5	25	250	2,500	25,000	250,000	2,500,000	25,000,000	250,000,000		
b	0.35	3.5	35	350	3,500	35,000	350,000	3,500,000	35,000,000	350,000,000		
d	0.40	4.0	40	400	4,000	40,000	400,000	4,000,000	40,000,000	400,000,000		
е	0.45	4.5	45	450	4,500	45,000	450,000	4,500,000	45,000,000	450,000,000		
f	0.50	5.0	50	500	5,000	50,000	500,000	5,000,000	50,000,000	500,000,000		
m	0.60	6.0	60	600	6,000	60,000	600,000	6,000,000	60,000,000	600,000,000		
n	0.70	7.0	70	700	7,000	70,000	700,000	7,000,000	70,000,000	700,000,000		
t	0.80	8.0	80	800	8,000	80,000	800,000	8,000,000	80,000,000	800,000,000		
у	0.90	9.0	90	900	9,000	90,000	900,000	9,000,000	90,000,000	900,000,000		



Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 - Carrier Tape Configuration, Embossed Plastic & Punched Paper (mm)

	Tape	Embosse	d Plastic	Punched Paper		
EIA Case Size	Size	7" Reel	13" Reel	7" Reel	13" Reel	
	(W)*	Pitch	(P ₁)*	Pitch	(P ₁)*	
01005 - 0402	8			2	2	
0603	8			2/4	2/4 /	
0805	8	4	4	4	4	
1206 - 1210	8	4	4	4	4	
1805 - 1808	12	4	4			
≥ 1812	12	8	8			
KPS 1210	12	8	8			
KPS 1812 and 2220	16	12	12			
Array 0612	8	4	4			

^{*}Refer to Figures 1 and 2 for W and P_1 carrier tape reference locations.

New 2 mm	Pitch Ree	l Options*
----------	-----------	------------

	Packaging Ordering Code (C-Spec)	Packaging Type/Options
1	C-3190	Automotive grade 7" reel unmarked
١	C-3191	Automotive grade 13" reel unmarked
	C-7081	Commercial grade 7" reel unmarked
	C-7082	Commercial grade 13" reel unmarked

^{* 2} mm pitch reel only available for 0603 EIA case size. 2 mm pitch reel for 0805 EIA case size under development.

Benefits of Changing from 4 mm to 2 mm Pitching Spacing

- · Lower placement costs.
- Double the parts on each reel results in fewer reel changes and increased efficiency.
- Fewer reels result in lower packaging, shipping and storage costs, reducing waste.

^{*}Refer to Tables 6 and 7 for tolerance specifications.



Figure 1 - Embossed (Plastic) Carrier Tape Dimensions




Table 6 – Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

	Constant Dimensions — Millimeters (Inches)											
Tape Size	D ₀	D ₁ Minimum Note 1	E ₁	P ₀	P ₂	R Reference Note 2	S ₁ Minimum Note 3	T Maximum	T ₁ Maximum			
8 mm		1.0 (0.039)				25.0 (0.984)						
12 mm	1.5 +0.10/-0.0 (0.059 +0.004/-0.0)	1.5 +0.10/-0.0 (0.059 +0.004/-0.0)	1.5	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)		
16 mm		(0.059)				(1.181)						
		,	Variable Dime	ensions — Mil	limeters (Inch	nes)						
Tape Size	Pitch	B ₁ Maximum Note 4	E ₂ Minimum	F	P ₁	T ₂ Maximum	W Maximum	A ₀ ,B ₀	& K ₀			
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)					
12 mm	Single (4 mm) and double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Note 5				
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5 ±0.05 (0.138 ±0.002)	12.0 ±0.10 (0.157 ±0.004)	4.6 (0.181)	16.3 (0.642)					

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of the embossment location and the hole location shall be applied independently of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 6.)
- 3. If S, < 1.0 mm, there may not be enough area for a cover tape to be properly applied (see EIA Standard 481, paragraph 4.3, section b.)
- 4. B_1 dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by A_{n} , B_{n} and K_{n} shall surround the component with sufficient clearance that:
 - (a) the component does not protrude above the top surface of the carrier tape.
 - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 3.)
 - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape
 - (e) for KPS product, A_0 and B_0 are measured on a plane 0.3 mm above the bottom of the pocket.
 - (f) see addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Figure 2 - Punched (Paper) Carrier Tape Dimensions




Table 7 - Punched (Paper) Carrier Tape Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)									
Tape Size	D ₀	E ₁	P ₀	P ₂	T ₁ Maximum	G Minimum	R Reference Note 2		
8 mm	1.5 +0.10 -0.0 (0.059 +0.004 -0.0)	1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	0.10 (0.004) maximum	0.75 (0.030)	25 (0.984)		
Variable Dimensions — Millimeters (Inches)									
Tape Size	Pitch	E2 Minimum	F	P ₁	T Maximum	W Maximum	A_0B_0		
8 mm	Half (2 mm)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	2.0 ±0.05 (0.079 ±0.002)	1.1 (0.098)	8.3 (0.327)	Note 1		
8 mm	Single (4 mm)			4.0 ±0.10 (0.157 ±0.004)		8.3 (0.327)			

- 1. The cavity defined by A_{n} , B_{n} and T shall surround the component with sufficient clearance that:
 - a) the component does not protrude beyond either surface of the carrier tape.
 - b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been
 - c) rotation of the component is limited to 20° maximum (see Figure 3.)
 - d) lateral movement of the component is restricted to 0.5 mm maximum (see Figure 4.)
 - e) see addendum in EIA Standard 481 for standards relating to more precise taping requirements.
- 2. The tape with or without components shall pass around R without damage (see Figure 6.)



Packaging Information Performance Notes


- 1. Cover Tape Break Force: 1.0 kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength		
8 mm	0.1 to 1.0 newton (10 to 100 gf)		
12 and 16 mm	0.1 to 1.3 newton (10 to 130 gf)		

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. Refer to EIA Standards 556 and 624.

Figure 3 – Maximum Component Rotation



Maximum Component Rotation Side View Maximum Tape Width (mm) Rotation (\bigcirc_{ς}) 20 8,12 16 - 5610 72 - 2005

Figure 4 - Maximum Lateral Movement




Figure 5 - Bending Radius







Figure 6 - Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 8 - Reel Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)								
Tape Size	A	B Minimum	С	D Minimum				
8 mm	178 ±0.20		13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)				
12 mm	(7.008 ±0.008) or	1.5 (0.059)						
16 mm	330 ±0.20 (13.000 ±0.008)	, ,	,					
Variable Dimensions — Millimeters (Inches)								
Tape Size	N Minimum	W ₁	W ₂ Maximum	W ₃				
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)					
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference				
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)					



Figure 7 - Tape Leader & Trailer Dimensions





Figure 8 - Maximum Camber





KEMET Electronics Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute - and KEMET specifically disclaims - any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.

KEMET is a registered trademark of KEMET Electronics Corporation.